

Linear Field Dependence of the Normal-State In-Plane Magnetoresistance of Sr_2RuO_4

R. Jin, Y. Liu

Department of Physics, The Pennsylvania State University, University Park, PA 16802

F. Lichtenberg

Center for Electronic Correlations and Magnetism, Augsburg University, D-86135 Augsburg, Germany

(February 1, 2008)

The transverse and longitudinal in-plane magnetoresistances in the normal state of superconducting Sr_2RuO_4 single crystals have been measured. At low temperatures, both of them were found to be positive with a linear magnetic-field dependence above a threshold field, a result not expected from electronic band theory. We argue that such behavior is a manifestation of a novel coherent state characterized by a spin pseudo gap in the quasi-particle excitation spectrum in Sr_2RuO_4 .

74.70.-b, 74.25.Fy, 74.25.Ha, 74.72.Yg

Since the discovery of superconductivity in Sr_2RuO_4 ,¹ isostructural with high- T_c cuprate $(\text{La,Sr})_2\text{CuO}_4$,^{1,2} this material has emerged as a new focus of superconductivity research.³ There has been a growing body of experimental evidence for a spin triplet (odd-parity) pairing in Sr_2RuO_4 ,⁴ including results obtained in muon spin relaxation,⁵ NMR Knight shift,⁶ electrical transport,⁷ proximity effect,⁸ and specific heat⁹ measurements. In the normal state, a highly anisotropic Fermi liquid behavior, characterized by a T^2 -dependence in the in- and out-of-plane resistivity (ρ_{ab} and ρ_c , respectively)³ and a cylindrical Fermi surface,¹⁰ was found for Sr_2RuO_4 at low temperatures. The enhancements of electronic specific heat and spin susceptibility are very similar to those found in ^3He ,^{3,4} suggesting that Sr_2RuO_4 is a strongly correlated system. At higher temperatures, however, the situation is not very clear. While ρ_c undergoes a non-metallic ($d\rho_c/dT < 0$) to metallic ($d\rho_c/dT > 0$) crossover around 130K,^{1,2} a similar feature is not seen in ρ_{ab} , a phenomenon yet to be fully understood.

Chemically, Sr_2RuO_4 is positioned in the vicinity of both ferromagnetic and antiferromagnetic orderings. In the Ruddlesden-Popper homologous series $\text{Sr}_{n+1}\text{Ru}_n\text{O}_{3n+1}$, as the single-layer ($n = 1$) member, Sr_2RuO_4 is a paramagnetic metal with no apparent local moment.¹¹ The infinite-layer ($n = \infty$) member, SrRuO_3 , is a ferromagnetic metal.¹² The $n = 2$ member of the series, $\text{Sr}_3\text{Ru}_2\text{O}_7$, which has been reported to be ferromagnetic by one group¹³ and antiferromagnetic by others,^{14,15} should be magnetic as well. On the other hand, if Sr^{2+} ions in Sr_2RuO_4 are replaced by Ca^{2+} , the resultant compound Ca_2RuO_4 , which is isostructural and isoelectronic to Sr_2RuO_4 , is an antiferromagnetic insulator.^{16,17} Being in the vicinity of these very different behaviours, Sr_2RuO_4 is likely to exhibit unusual electronic and magnetic properties.

The normal-state properties of Sr_2RuO_4 can be probed by magnetoresistance (MR) measurements.¹⁸ The normal-state MR of Sr_2RuO_4 was first measured at 20mK in the context of determining the Fermi surface of this material through the Shubnikov-de Haas oscillations.¹⁹

However, no field dependence of MR was identified in that work. More recently, Hussey *et al.* have measured both c -axis and in-plane normal-state MR of Sr_2RuO_4 , focusing primarily on the c -axis MR ($\Delta\rho_c/\rho_c = (\rho_c(H) - \rho_c(0))/\rho_c(0)$) at relatively high temperatures.²⁰ The in-plane MR ($\Delta\rho_{ab}/\rho_{ab} = (\rho_{ab}(H) - \rho_{ab}(0))/\rho_{ab}(0)$) was measured only in transverse configuration for one sample, without a detailed analysis of its field dependence over the entire temperature range. Longitudinal in-plane MR results were not available in literature prior to the present study. In this paper, we report results of our systematic study of the normal-state in-plane MR for Sr_2RuO_4 in both transverse and longitudinal configurations. Our work has revealed previously unknown features in in-plane MR, strongly suggesting a novel behavior in the normal state of Sr_2RuO_4 .

Single crystals used in this study were grown by a floating-zone method with details described elsewhere.² Resistance measurements show a superconducting transition temperature (T_c) of 0.84K. MR measurements were carried out in a ^3He cryostat. The temperature was measured using a Lakeshore Cernox 1030 thermometer with relative temperature corrections, due to magnetic field, typically 0.15% at 4.2 K and -0.023% at 77.8K and 8.0T.²¹ For in-plane MR and Hall measurements, we used four rectangular shaped single crystals with dimensions around $1.2 \times 1.0 \times 0.01$, $0.9 \times 0.4 \times 0.08$, $0.8 \times 0.2 \times 0.07$, and $0.6 \times 0.3 \times 0.05\text{mm}^3$, respectively. For each sample, two current contacts covering the opposite ends and four voltage contacts on the two sides of the crystal were prepared. All RuO_2 layers were electrically shorted along the c -axis to ensure a homogeneous current distribution. For transverse and longitudinal MR measurements, the magnetic field H was applied perpendicular and parallel to the injected current I , respectively. In order to exclude the Hall contribution to MR, only the symmetric part of $\Delta\rho_{ab}(H) = \rho_{ab}(H) - \rho_{ab}(0)$ under field reversal was included. For in-plane Hall measurements, the magnetic field was applied parallel to c -axis with a current bias applied along the ab -plane. The Hall voltage V_H , which contains only the asymmetric contributions under

the field reversal, was found to vary linearly with H up to 5T. By fitting $V_H(H)$ data in the linear regime using $V_H = R_H \cdot H \cdot I/d$ (d is the thickness of the sample), the in-plane Hall coefficient R_H was obtained.

The transverse in-plane MR, $\Delta\rho_{ab}^\perp/\rho_{ab}$ ($H \perp I$), between 0 and 7.3T at various temperatures is shown in Fig. 1. Similar results have been obtained in separate samples. $\Delta\rho_{ab}^\perp/\rho_{ab}$ is seen to be positive, growing rapidly in magnitude with decreasing T . At low fields, $\Delta\rho_{ab}^\perp/\rho_{ab}$ at a fixed temperature is very small, which can be described by the sum of a linear and a quadratic term. When H exceeds a threshold value H_0 , $\Delta\rho_{ab}^\perp/\rho_{ab} = K_S(H - H_0)$, where K_S and H_0 are functions of temperature. The solid lines in Fig. 1 represent fits to the data above H_0 using this form. The temperature dependence of H_0 is shown in the inset of Fig. 1. We note that in Ref. 20, results on $\Delta\rho_{ab}^\perp/\rho_{ab}$, plotted against H^2 , were presented. While $\Delta\rho_{ab}^\perp/\rho_{ab}$ might be quadratic in H at the two highest temperatures shown (56K and 82K), a deviation from this behavior can be seen at all other temperatures. (We have re-plotted the low temperature data against H and found both the magnitude and the field dependence of $\Delta\rho_{ab}^\perp/\rho_{ab}$ given in Ref. 20 are in agreement with those obtained in the present study at overlapping temperatures.)

Within the band theory for solids, MR is proportional to $(H/\rho(0))^2$ in the low-field limit.¹⁸ Linear MR can be expected only in some special circumstances. For example, a square Fermi surface can lead to linear MR due to the presence of the sharp corners.¹⁸ Local-density approximation calculations have shown that the Fermi surface of Sr_2RuO_4 consists of three roughly cylindrical-like sheets with no such sharp corners,²² thus excluding this from being the origin of the observed linear MR. For systems with multi-band electronic structure involving two types of charge carriers, the field dependence of MR can be written as $\Delta\rho/\rho(0) = aH^2/(b + cH^2)$ where a , b , and c are positive, field-independent quantities determined by the relaxation rates of each type of carriers.²³ It is clear that this expression will not lead to $\Delta\rho/\rho(0) \sim H$ as observed experimentally. In some elemental metals (such as K, In, and Al), linear MR has been found and attributed to the boundary and disorder effects.¹⁸ Since superconductivity in Sr_2RuO_4 is extremely sensitive to the amount of disorder,⁷ the linear $\Delta\rho_{ab}^\perp/\rho_{ab}$, found reproducibly in superconducting Sr_2RuO_4 with $\rho_{ab}(0) \approx 1\mu\Omega\text{cm}$, is unlikely due to effects of the impurities and/or structural defects.

Linear MR was observed previously in heavy fermion CeCu_6 at very low temperatures.²⁴ In another heavy fermion compound, UPt_3 , the MR was found²⁵ to be positive and proportional to $H^{1.25}$. The observed linear MR was interpreted as being a consequence of the opening of a pseudo gap in a coherent state formed at low temperatures.²⁶ In this picture, the pseudo gap is suppressed by the magnetic field, resulting in enhanced scattering rates and therefore positive MR. NMR studies of Sr_2RuO_4 provided the first hint that a coherent

normal state may also be present in this material at low temperatures. The emergence of such a state is signaled by a sharp change of slope in $1/T_1$ vs. temperature curve for both ^{101}Ru and planar ^{17}O sites around 80K.²⁸ Our in-plane MR results also indicate that this temperature is special for Sr_2RuO_4 . As shown in Fig. 2, a sign change from positive to negative in $\Delta\rho_{ab}^\perp/\rho_{ab}$ is seen between 70-80 K, similar to what has been observed in c -axis MR.²⁰ It should be noted that the range of the data scattering in $\Delta\rho_{ab}^\perp/\rho_{ab}$ at 7.3 T is around 0.004%. The corrections in temperature due to the MR of the thermometer is around -0.016% at 87 K and 8.0 T,²¹ which cannot lead to the observed sign change in $\Delta\rho_{ab}^\perp/\rho_{ab}$. While the physical origin of the sign reversal in MR has not been understood at the present time, it is not inconceivable that this is associated with the emergence of a coherent normal state in Sr_2RuO_4 at low temperatures. As will be argued later, such a state may be accompanied by the opening of a pseudo gap in the quasi-particle excitation spectrum. Similar to CeCu_6 , an applied magnetic field suppresses the pseudo gap, leading to linear in-plane MR for Sr_2RuO_4 .

The in-plane Hall coefficient R_H of Sr_2RuO_4 , should be subject to the same scattering processes as that for the in-plane MR. An interesting question is whether R_H will reflect the presence of a pseudo gap in the quasi-particle excitation spectrum. The in-plane R_H was measured for one of our samples in the same magnetic field and current configuration as that for the transverse in-plane MR. The results are shown in Fig. 3. The Hall coefficient is negative at high temperatures, changing its sign around 130K, which is roughly where ρ_c undergoes a nonmetallic-metallic crossover. It reaches a maximum between 70-80K before changing its sign again around 30K. Prior to the present work, the Hall coefficient R_H of Sr_2RuO_4 has been measured on crystals prepared by different groups.^{28,29} Our results agree well with those published earlier, indicating that features shown in $R_H(T)$ are intrinsic. In Ref. 19, an isotropic- ℓ approximation within the multi-band picture of Sr_2RuO_4 was used to calculate the low temperature limit ($T < 1\text{K}$) of R_H with band parameters obtained from quantum oscillations. The calculated result agrees with the experimental value. On the other hand, a manybody-theory-based calculation of $R_H(T)$ has also been carried out,³⁰ yielding a result that is consistent with experimental observations. This suggests that an account for behaviors in R_H beyond band theory is still possible, especially for $T > 1\text{K}$ where the isotropic- ℓ approximation did not seem to work.¹⁹ It is interesting to note that the characteristic temperature where R_H shows a maximum coincides with that below which we believe the pseudo gap emerges. Whether the maximum in R_H is another signature for the opening of a pseudo gap in Sr_2RuO_4 , and how strongly the presence of such a gap will affect R_H , are issues to be resolved.

In order to infer the relative contribution of the orbital and spin motions to MR and the physical origin of this pseudo gap, we have measured the longitudinal in-plane

MR of Sr_2RuO_4 . As shown in Fig. 4, the longitudinal in-plane MR $\Delta\rho_{ab}^{\parallel}/\rho_{ab}$ also revealed a linear behavior above H_0 , which increases with increasing temperature (see the inset of Fig. 4). More striking is that the magnitude of $\Delta\rho_{ab}^{\parallel}/\rho_{ab}$ is greater than that of $\Delta\rho_{ab}^{\perp}/\rho_{ab}$ below approximately 10K, indicating that the spin contribution to the in-plane MR is important. Therefore, the pseudo gap may be of spin origin. Results obtained in NMR ^{17}O Knight shift measurements in Sr_2RuO_4 ^{27,31} point to the same direction. When the ^{17}O Knight shift results were decomposed into spin susceptibilities of three Ru d-orbitals, d_{xy} , d_{xz} , and d_{yz} , a broad maximum around 40K was found. This is consistent with uniform susceptibility results where a broad peak was seen around the same temperature.¹¹ The decrease of spin susceptibility at low temperatures may then be taken as an indication of the opening of a pseudo gap in the spin excitation spectrum.

It has been suggested theoretically that the spin fluctuations in Sr_2RuO_4 are predominantly ferromagnetic.^{4,32} Experimentally, $1/T_1$ obtained from the NMR measurements for both O(1) and Ru sites shows an identical temperature dependence.²⁷ In general, $1/T_1$ can be expressed by the sum of $\mathbf{q}$ -dependent imaginary part of the dynamical electron susceptibility with appropriate form factors, which should have different $\mathbf{q}$ -dependence for ^{101}Ru and planar ^{17}O sites, leading to different temperature dependence in their respective $1/T_1$. However, if the dynamical electron susceptibility has a sharp peak around $\mathbf{q} = (0, 0)$, corresponding to ferromagnetic fluctuations, then the above mentioned behavior in $1/T_1$ can be explained. On the other hand, this scenario will lead to negative MR,¹⁸ which contradicts the experimental observation of positive MR.

Results obtained in inelastic neutron scattering (INS) measurements carried out recently on Sr_2RuO_4 ³³ have resolved this apparent contradiction between NMR and magnetotransport results. In this experiment, incommensurate magnetic spin fluctuations located at $\mathbf{q}_0 = (\pm 0.6/a, \pm 0.6/a, 0)$, originally predicted by band calculations,³⁴ were found at low temperatures. The intrinsic $\mathbf{q}$ -width for these incommensurate fluctuations was found to be narrow ($\Delta\mathbf{q} = 0.13 \pm 0.02\text{\AA}$ at 10K). The temperature dependence of $1/T_1$ observed in NMR can be reconstructed from the INS results, confirming that the dominating spin fluctuations are incommensurate rather than ferromagnetic as suggested in Ref. 26. The energy dependence of the imaginary part of the dynamic susceptibility at $\mathbf{q}_0$, which measures the dissipation of the spin fluctuations, shows a gradual drop below 7meV, indicating the presence of a gap in the spin excitation spectrum. We note here that this energy scale (7 meV) agrees well with the value of the pseudo gap inferred from the temperature dependence of other physical quantities such as $1/T_1$ and MR.

Physical insight into the nature of the normal state of Sr_2RuO_4 can be obtained from the high-pressure experi-

ments. It was shown that the superconducting transition temperature T_c was suppressed by an applied pressure p .³⁵ By extrapolating results obtained up to 1.2 GPa, T_c is expected to become zero around $p_c \approx 3$ GPa. In normal state, ρ_{ab} was found to vary non-monotonically with p at low T .³⁶ With increasing p , ρ_{ab} first increases, and then decreases as p was increased further above a threshold value, close to 3 GPa. At 8 GPa, ρ_{ab} was found to show a $T^{4/3}$ -dependence, characteristic of a two-dimensional electronic system close to a ferromagnetic quantum critical point.³⁷ Based on this, we propose the following phase diagram for Sr_2RuO_4 , shown schematically in Fig.5. At $T = 0$ K, a direct superconductor (SC)-to-ferromagnetic metal (FM) transition, tuned by pressure, occurs at $p = p_c \approx 3$ GPa. At low T and low p , Sr_2RuO_4 is superconducting. A pseudo gap regime emerges above T_c , similar to the quantum spin disordered regime discussed in quantum critical phenomena.³⁸ As p is further increased, the pseudo gap is suppressed, leading to an increase in ρ_{ab} , as observed experimentally.³⁶ When the system enters the fluctuating regime at a finite T , ρ_{ab} decreases with the increasing T since the system is driven towards a ferromagnetic state. We suggest that the magnetic field similarly suppresses the pseudo gap, resulting in a positive MR. In this picture, as T increases, a larger threshold field (H_0) is needed to overcome the thermal smearing so that linear MR can be observed, consistent with our experimental observations.

A pseudo gap has been observed in high- T_c cuprate superconductors.³⁹ However, the origin and physical consequences of pseudo gap in high- T_c materials may be different from that in Sr_2RuO_4 . The in-plane MR observed in $(\text{La}, \text{Sr})_2\text{RuO}_4$ ⁴⁰ is positive, but not linear in field dependence. When the pseudo gap opens, the Hall coefficient was found to become strongly temperature-dependent.⁴¹ A suppression in resistivity was found in underdoped $(\text{La}, \text{Sr})_2\text{RuO}_4$ as the pseudo gap opened.⁴⁰ A similar feature has not been observed in Sr_2RuO_4 . As mentioned above, the pseudo gap in Sr_2RuO_4 is present only in a small portion of the Fermi surface. The magnitude of the gap is also small as compared with that of the high- T_c cuprates, resulting in unobservable effects in ρ_{ab} and ρ_c .

Finally we briefly mention our $\Delta\rho_c/\rho_c$ results which will be discussed in detail in a future publication. As mentioned above, previously published work on $\Delta\rho_c/\rho_c$ of Sr_2RuO_4 was focused on relatively high-temperature (>22 K) behavior although data obtained at 3.6 K were also shown.²⁰ The magnitude of our longitudinal c -axis MR, $\Delta\rho_c^{\parallel}/\rho_c$, is comparable with that of the transverse MR, $\Delta\rho_c^{\perp}/\rho_c$. The difference, $\Delta\rho_c^{\perp}/\rho_c - \Delta\rho_c^{\parallel}/\rho_c$, the "pure" orbital MR, has very good H^2 -dependence. A sign reversal from positive at low T to negative at high T was found in both $\Delta\rho_c^{\perp}/\rho_c$ and $\Delta\rho_c^{\parallel}/\rho_c$ around 75 K, consistent with previous observations.²⁰ However, different from the previous study, we found that $\Delta\rho_c(H)/\rho_c = \alpha H^2 - \beta H^4$ (where α and β are constants), actually de-

scribes well our $\Delta\rho_c^\perp/\rho_c$ and $\Delta\rho_c^\parallel/\rho_c$ data.⁴²

In summary, we have studied the magnetic field dependence of in-plane MR of Sr_2RuO_4 up to 7.3T. The linear positive transverse and longitudinal in-plane MR, not expected from band theory, has been found above a threshold field at low temperatures. We argue that such behavior is a manifestation of a coherent pseudo gap state in Sr_2RuO_4 formed at low temperatures. Theoretical input is needed to fully understand the experimental results.

We would like to acknowledge helpful discussions with P. Coleman, N. Hussey, T. Imai, J. Jain, H. Kawano, Y. B. Kim, and G. Lonzarich, technical assistance from Yu. Zadorozhny, and finally many important contributions of D. Schlom to this project. This work is supported in part in the US by NSF through grants DMR-9702661 and ECS-9705839 and by the BMBF (Project number 13N6918/1) in Germany.

- ¹ Y. Maeno, *et al.*, Nature **372**, 532 (1994).
- ² F. Lichtenberg, *et al.*, Appl. Phys. Lett. **60**, 1138 (1992).
- ³ Y. Maeno, Cze. J. Phys. **46**, Suppl. S6, 3097 (1996).
- ⁴ T.M. Rice and M. Sigrist, J. Phys.: Cond. Matt. **7**, L643 (1995).
- ⁵ G.M. Luke, *et al.*, Nature **394**, 558 (1998).
- ⁶ K. Ishida, *et al.*, Nature **396**, 658 (1998).
- ⁷ A.P. Mackenzie, *et al.*, Phys. Rev. Lett. **80**, 161(1998).
- ⁸ R. Jin, *et al.*, Phys. Rev. B **59**, 4433 (1999).
- ⁹ S. Nissishizaki, *et al.*, J. Phys. Soc. Jpn. **67**, 560(1998).
- ¹⁰ A.P. Mackenzie, *et al.*, Phys. Rev. Lett. **76**, 3786 (1996).
- ¹¹ Y. Maeno *et al.*, J. Phys. Soc. Japan. **66**, 1405 (1997).
- ¹² A. Callaghan, C.W. Moeller, and R. Ward, Inorganic Chem. **5**, 1572 (1966).
- ¹³ G. Cao, S. McCall and J.E. Crow, Phys. Rev. B **55**, R672 (1997).
- ¹⁴ R.J. Cava, *et al.*, J. of Solid State Chem. **116**, 141 (1995).
- ¹⁵ Y. Maeno, S. Nakatsuji, and S. Ikeda, Proc. Taniguchi Symp. on Phys. and Chem. of Transition Metal Oxides, Springer Series in Solid-State Sci., Vol. **125** (1998).
- ¹⁶ G. Cao, *et al.*, Phys. Rev. B **56**, R2916 (1997).
- ¹⁷ S. Nakatsuji, S. Ikeda, and Y. Maeno, J. Phys. Soc. Jpn. **66**, 1868 (1997).
- ¹⁸ A.B. Pippard, *Magnetoresistance in Metals*, (Cambridge Univ. Press, 1989).
- ¹⁹ A.P. Mackenzie *et al.*, Physica C **263** 1996 (1996).
- ²⁰ N.E. Hussey, *et al.*, Phys. Rev. B **57**, 5505 (1998).
- ²¹ B.L. Brand, D.W. Liu and L.G. Rubin **70**, 104 (1999).
- ²² T. Oguchi, Phys. Rev. B **51**, 1385 (1995); D.J. Singh, Phys. Rev. B **52**, 1358 (1995).
- ²³ J.M. Ziman, *Principles of the Theory of Solids*, 2nd Ed., (Cambridge Univ. Press, 1972).
- ²⁴ P.T. Coleridge, J. Phys. F: Met. Phys. **17**, L79 (1987).
- ²⁵ G.R. Stewart, Rev. Mod. Phys. **56**, 755 (1984).
- ²⁶ B. H. Brandow, Phys. Rev. B **33**, 215 (1986).

- ²⁷ T. Imai *et al.*, Phys. Rev. Lett. **81**, 3006 (1998).
- ²⁸ N. Shirakawa *et al.*, J. Phys. Soc. Jpn. **64**, 1072 (1995).
- ²⁹ A. P. Mackenzie *et al.*, Phys. Rev. B **54**, 7425 (1996).
- ³⁰ M. Miyazawa, H. Kontani, and K. Yamada, preprint.
- ³¹ H. Mukuda, *et al.*, J. Phys. Soc. Jpn. **67**, 3945 (1998).
- ³² I.I. Mazin and D.J. Singh, Phys. Rev. Lett. **79**, 733 (1997).
- ³³ Y. Sidis *et al.*, preprint (cond-mat/9904348, 23 Apr., 1999).
- ³⁴ I.I. Muzin and D.J. Singh, preprint (cond-mat/9902193, 12 Feb., 1999).
- ³⁵ N. Shirakawa, *et al.*, Phys. Rev. B **56**, 7890 (1997).
- ³⁶ K. Yoshida, *et al.*, Phys. Rev. B **58**, 15062 (1998).
- ³⁷ C. Pfleiderer, *et al.*, Phys. Rev. B **55**, 8330 (1997).
- ³⁸ J.A. Hertz, Phys. Rev. B **14**, 1165 (1976); A.J. Millis, Phys. Rev. B **48**, 7183 (1993).
- ³⁹ For a recent review, see T. Timusk and B. Statt, Rep. Prog. Phys. **62**, 61 (1999).
- ⁴⁰ N. W. Preyer *et al.*, Phys. Rev. B **44**, 407 (1991); A. Lacerda, *et al.*, Phys. Rev. B **49**, 9097 (1994); J. M. Harris, *et al.*, Phys. Rev. Lett. **75**, 1391 (1995); T. Kimura, *et al.*, Phys. Rev. B **53**, 8733 (1996).
- ⁴¹ B. Batlogg, *et al.*, Physica C **140**, 235 (1994).
- ⁴² R. Jin, *et al.*, J. Phys. Chem. Solids **59**, 2215 (1998).

FIG. 1. In-plane transverse MR, $\Delta\rho_{ab}^\perp/\rho_{ab}$ ($H \perp ab$, $I \parallel ab$), for Sr_2RuO_4 . The solid lines are linear fits to the data (see text). $H_0(T)$ is shown in the inset.

FIG. 2. In-plane transverse MR for Sr_2RuO_4 at temperatures close to 75K.

FIG. 3. In-plane Hall coefficient $R_H(T)$ with a broad peak around 70-80K.

FIG. 4. In-plane longitudinal MR $\Delta\rho_{ab}^\parallel/\rho_{ab}$ ($H \parallel ab$, $I \parallel ab$) for Sr_2RuO_4 . The solid lines are linear fits to the data. $H_0(T)$ is shown in the inset. Note that $\Delta\rho_{ab}^\parallel/\rho_{ab}$ is larger than $\Delta\rho_{ab}^\perp/\rho_{ab}$ below 10K.

FIG. 5. Schematic phase diagram for Sr_2RuO_4 , where SC denotes the superconducting while FM the ferromagnetic metal phase. A zero-temperature SC-FM transition at $p = p_c \approx 3$ GPa is indicated (see text).

This figure "Fig.1.jpg" is available in "jpg" format from:

<http://arXiv.org/ps/cond-mat/9908280v1>

This figure "Fig.2.jpg" is available in "jpg" format from:

<http://arXiv.org/ps/cond-mat/9908280v1>

This figure "Fig.3.jpg" is available in "jpg" format from:

<http://arXiv.org/ps/cond-mat/9908280v1>

This figure "Fig.4.jpg" is available in "jpg" format from:

<http://arXiv.org/ps/cond-mat/9908280v1>

This figure "Fig.5.jpg" is available in "jpg" format from:

<http://arXiv.org/ps/cond-mat/9908280v1>